

**TECHNICHE UK LTD
CROWN HOUSE
30 COMMERCE ROAD
BRENTFORD
MIDDLESEX
TW8 8LE**

The following sample(s) was/were submitted and identified by/on behalf of the client as:

| | |
|---------------------------|--|
| Retailer | Not Specified |
| Description of article | SUPER ABSORBENT FIBRE (SAF) |
| Retailer style number | HYPERKEWL PLUS |
| Retailer Standard Number | UNKNOWN |
| Order No./ Buyer | TechNiche UK |
| Quality/Fibre Composition | ACRYLIC BASED MONOMER & METHYLACRYLIC ACID |
| Date Sample(s) Received: | 08 September 2017 |

Test

Dimensional Stability to Washing @ 60°C

Remarks

Tests as requested by the customer

Signature

For and on behalf of
SGS Leicester Ltd.

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer: Techniche UK Ltd **Test Report No:** 134539B (Replaces 134539A)

Test Results

AFTER 10 WASHES

Dimensional Stability to Washing
Wash: 2A 60 °C Dry: Flat

BS EN ISO 6330:2001/ BS EN ISO 5077:2008/ BS EN ISO 3759:2011

Length (%) -2.9

Width (%) +0.4

AFTER 20 WASHES

Dimensional Stability to Washing
Wash: 2A 60 °C Dry: Flat

BS EN ISO 6330:2001/ BS EN ISO 5077:2008/ BS EN ISO 3759:2011

Length (%) -3.1

Width (%) +0.2

AFTER 30 WASHES

Dimensional Stability to Washing
Wash: 2A 60 °C Dry: Flat

BS EN ISO 6330:2001/ BS EN ISO 5077:2008/ BS EN ISO 3759:2011

Length (%) -3.3

Width (%) +0.5

AFTER 40 WASHES

Dimensional Stability to Washing
Wash: 2A 60 °C Dry: Flat

BS EN ISO 6330:2001/ BS EN ISO 5077:2008/ BS EN ISO 3759:2011

Length (%) -4.1

Width (%) +0.5

AFTER 50 WASHES

Dimensional Stability to Washing
Wash: 2A 60 °C Dry: Flat

BS EN ISO 6330:2001/ BS EN ISO 5077:2008/ BS EN ISO 3759:2011

Length (%) -4.1

Width (%) +0.4

End of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only